

**THERMAL INSULATION AND AIR BARRIER**  
 ESR-699 | CSI Section: 07 21 00

**PRODUCT DESCRIPTION**

Accufoam CC is a two-component, one-by-one-by-volume spray-applied polyurethane foam. Accufoam CC is a high-yield, medium-density, spray-applied insulation foam, and is designed to provide good thermal performance and a significant control of air infiltration of an air-barrier assembly.



**PRODUCT DATA**

PROPERTY	TEST METHOD	VALUE
R-VALUE @ 1"	ASTM C 518	6.52
R-VALUE @ 3.5"	ASTM C 518	23
CORE DENSITY	ASTM D 1622	1.8-2.0 pcf
OPEN-CELL CONTENT	ASTM D 6226	<5%
DIMENSIONAL STABILITY	ASTM D 2126	<8.6%
TENSILE STRENGTH	ASTM D 1623	53.5 psi
COMPRESSIVE STRENGTH	ASTM D 1621	31.75 pcf
AIR PERMEANCE	ASTM E 2178	<0.02
SURFACE BURNING CHARACTERISTICS	ASTM E 84	Class-1
CRITICAL RADIANT HEAT FLUX	ASTM E 970	Pass
WATER VAPOR PERMEANCE	ASTM E 96	1.77 perms at 1
RE-ENTRY PERIOD		4-Hour
RE-OCCUPANCY PERIOD		24-Hours
VISCOSITY-ISO AT 77F (CPS)		200
VISCOSITY-RESIN AT 77F		720

**BURN CHARACTERISTICS**

PROPERTY	TEST METHOD	VALUE
FLAME SPREAD INDEX	ASTM E 84	< 25
SMOKE DEVELOPMENT	ASTM E 84	< 450

**THERMAL BARRIER NFPA286**

TYPE	WFT	WALL	CEILING	APPLICATION RATE
DC315	19 MIL MIN	5.5 INCH MAX	9.5 INCH MAX	.25 GAL/100 SQ FT

**IGNITION BARRIER AC377X**

Complies with the applicable requirements of AC377 Appendix X for use in attics and crawl spaces without a prescriptive ignition barrier

## TEMPERATURE GRADES

REACTIVITIES AVAILABLE	AMBIENT TEMPERATURE RANGE
SUMMER +	> 95°F
SUMMER	70°F – 95°F
REGULAR	50°F – 70°F
WINTER	30°F – 50°F
POLAR	20°F – 35°F

## APPLICATION PARAMETERS

STORAGE TEMPERATURE	60° – 90°
AMBIENT TEMPERATURE	40° – 120°
SUBSTRATE TEMPERATURE	40° – 120°
MOISTURE CONTENT OF SUBSTRATE	Less than 19%
MAXIMUM LIFT PER PASS	Not to exceed 3"

## EQUIPMENT SETTINGS

PRE-HEATER: (A) COMPONENT – ISO	110° – 130°
PRE-HEATER: (B) COMPONENT – RESIN	110° – 130°
HOSE HEAT	110° – 130°
FLUID PRESSURE – DYNAMIC	1100 – 1400 psi
MIXING RATIO	1:1 by Volume
RECOMMENDED MIX CHAMBER SIZE	10-15 lbs./minute (i.e. 01-Graco AR4242)
STORAGE STABILITY	6 Months

*\*The values represented in the Equipment Settings chart provides initial optimum settings. Actual operating ranges will vary as ambient air; humidity, moisture, and substrate temperatures vary. Extreme conditions will affect the yield, adhesion and cured physical properties of the foam. Applicator must make adjustments as conditions vary.*

*Disclaimer: The data herein is to assist customers who desire to use our products to determine if the products are safe and suitable for their applications. The data presented herein is not intended for use by non-professional applicators, or those persons who do not purchase or utilize this product in the normal course of their business. Customers further assume full responsibility for quality control, testing and determining whether the products are suitable for each individual application. To the best of Creative Polymers knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. NO WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE SUED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF CREATIVE POLYMER'S TERMS AND CONDITIONS OF SALE.*